

CORROSIONS-RESISTANT STEELS - AUSTENITIC STEELS AND NON MAGNETIC STEELS

Available Product Variants

Plates

Product Description

Austenitic chromium-nickel stainless steel with excellent corrosion resistance in boiling nitric acid (concentration up to 80%).
Fertiliser plants and production units for nitric acid, as well as for the reprocessing of nuclear fuel.

Process Melting

ESR

Applications

- > Components for Chemical plants (incl. LNG, FGD, Urea, LDPE, etc.)
- > Other Oil and Gas + CPI components
- > Tubular Products, Flanges, Fittings

Technical data

| Material designation | |
|----------------------|-----|
| 1.4335 | SEL |
| S31002 | UNS |
| S31008 | |

Chemical composition (wt. %)

| C | Si | Mn | Cr | Mo | Ni |
|---------|-----|-----|----|--------|----|
| ≤ 0,018 | 0.1 | 1.2 | 25 | ≤ 0,10 | 21 |

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at

<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.