

CORROSION RESISTANT STEELS - MARTENSITIC, SEMI- MARTENSITIC AND FERRITIC STEELS

Available Product Variants

Plates

Product Description

Chromium stainless steel for turbine components.

Good cold formability. In a ground and polished surface-finish, corrosion resistant against water and steam.

Applications

➤ Other Power Generation Components

Technical data

Material designation		Standards	
1.4002	SEL	A240	ASTM
X6CrAl13	EN		
S40500	UNS		
AISI:405	AISI		

Chemical composition (wt. %)

C	Si	Mn	Cr	Al
≤ 0,08	0.4	0.4	12.5	0.2

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at

<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.